

TECHNICAL DATA

Material:	Engineered Wood 15/4mm (wear layer: 3mm)
Dimensions:	2200 x 260 x 15/4mm 4 pieces/box ; 2.288 sqm/box ; 60 boxes per pallet
Weight per Box:	22kg /box
Weight per Pallet:	1320 kgs

SKU	ENG-CD-2001=NF01
Colour	Clifton-260
size	260 x 15/4 x 2200mm
Grade	DE
Type of finish	Light Brushed & Supper Matt UV Oiled
Stained Color	Stained color
Profile	T&G
Edge	Bevelled
Thickness	15mm
Width	260mm
Length	2200mm (75%)
Wear Layer	4mm
Backing	Eucalyptus & Poplar
Top Layer	Oak
Pack size m2	4pcs/2.288
Packs per pallet	60 (4X15)
Structure	Engineered Multi-layer
Width Tolerance	+/-0.2mm
Gloss level	10%+/-5%
Live knot & filler colour	Not limited, Brown filler
Dead knot	<50mm Filled 50MM
Colour difference	Allowed
Sapwood	not limited,Color reparing acceptable
Grain	All Grain Patterns Acceptable
Split	Hairline Split < 3x500mm
FSC/PEFC	NO
Formaldehyde	E1
Pentachlorophenol Emissions	0.02-0.04mg/L
Moisture Content	6-8%
Fire Classification	Dfl-sI
Hardness Rating	2H

TECHNICAL DATA

SKU	ENG-CD-2002=NF04
Colour	Knysna-260
size	260 x 15/4 x 2200mm
Grade	DE
Type of finish	Light Brushed & Supper Matt UV Oiled
Stained Color	stained color ,invisible lacquered
Profile	T&G
Edge	Bevelled
Thickness	15mm
Width	260mm
Length	2200mm (75%)
Wear Layer	4mm
Backing	Eucalyptus & Poplar
Top Layer	Oak
Pack size m2	4pcs/2.288
Packs per pallet	60 (4X15)
Structure	Engineered Multi-layer
Width Tolerance	+/-0.2mm
Gloss level	10%+/-5%
Live knot & filler colour	Not limited, Brown filler
Dead knot	<50mm Filled 50MM
Colour difference	Allowed
Sapwood	not limited,Color reparing acceptable
Grain	All Grain Patterns Acceptable
Split	Hairline Split < 3x500mm
FSC/PEFC	NO
Formaldehyde	E1
Pentachlorophenol Emissions	0.02-0.04mg/L
Moisture Content	6-8%
Fire Classification	Dfl-s1
Hardness Rating	2H

TECHNICAL DATA

SKU	ENG-CD-2003=NF05
Colour	Bakoven-260
size	260 x 15/4 x 2200mm
Grade	DE
Type of finish	Light Brushed & Supper Matt UV Oiled
Stained Color	stained color ,invisible lacquered
Profile	T&G
Edge	Bevelled
Thickness	15mm
Width	260mm
Length	2200mm (75%)
Wear Layer	4mm
Backing	Eucalyptus & Poplar
Top Layer	Oak
Pack size m2	4pcs/2.288
Packs per pallet	60 (4X15)
Structure	Engineered Multi-layer
Width Tolerance 幅宽公差	+/-0.2mm
Gloss level 亮度	10%+/-5%
Live knot & filler colour 活节	Not limited, Brown filler
Dead knot 死节	<50mm Filled 50MM
Colour difference	Allowed
Sapwood	not limited,Color reparing acceptable
Grain	All Grain Patterns Acceptable
Split	Hairline Split < 3x500mm
FSC/PEFC	NO
Formaldehyde	E1
Pentachlorophenol Emissions	0.02-0.04mg/L
Moisture Content	6-8%
Fire Classification	Dfl-s1
Hardness Rating	2H

TECHNICAL DATA

SKU	ENG-CD-2004=NF06
Colour	Franschoek-260
size	260 x 15/4 x 2200mm
Grade	DE
Type of finish	Light Brushed & Supper Matt UV Oiled
Stained Color	Natural color
Profile	T&G
Edge	Bevelled
Thickness	15mm
Width	260mm
Length	2200mm (75%)
Wear Layer	4mm
Backing	Eucalyptus & Poplar
Top Layer	Oak
Pack size m2	4pcs/2.288
Packs per pallet	60 (4X15)
Structure	Engineered Multi-layer
Width Tolerance	+/-0.2mm
Gloss level	10%+/-5%
Live knot & filler colour	Not limited, Brown filler
Dead knot	<50mm Filled 50MM
Colour difference	Allowed
Sapwood	not limited,Color reparing acceptable
Grain	All Grain Patterns Acceptable
Split	Hairline Split < 3x500mm
FSC/PEFC	NO
Formaldehyde	E1
Pentachlorophenol Emissions	0.02-0.04mg/L
Moisture Content	6-8%
Fire Classification	Dfl-s1
Hardness Rating	2H

TECHNICAL DATA

SKU	ENG-CD-2005=NF02
Colour	Constantia-260
size	260 x 15/4 x 2200mm
Grade	DE
Type of finish	Light Brushed & Supper Matt UV Oiled
Stained Color	Stained color,Wipe Glas with hand
Profile	T&G
Edge	Bevelled
Thickness	15mm
Width	260mm
Length	2200mm (75%)
Wear Layer	4mm
Backing	Eucalyptus & Poplar
Top Layer	Oak
Pack size m2	4pcs/2.288
Packs per pallet	60 (4X15)
Structure	Engineered Multi-layer
Width Tolerance	+/-0.2mm
Gloss level	10%+/-5%
Live knot & filler colour	Not limited, Brown filler
Dead knot	<50mm Filled 50MM
Colour difference	Allowed
Sapwood	not limited,Color reparing acceptable
Grain	All Grain Patterns Acceptable
Split	Hairline Split < 3x500mm
FSC/PEFC	NO
Formaldehyde	E1
Pentachlorophenol Emissions	0.02-0.04mg/L
Moisture Content	6-8%
Fire Classification	Dfl-s1
Hardness Rating	2H